

PRODUCT DATA SHEET

SikaCor®-202 ET

TWO COMPONENT EPOXY TOPCOAT

DESCRIPTION

SikaCor®-202 ET is a high build two component polyamide cured recoatable epoxy topcoat.

USES

- As a topcoat in epoxy paint systems on structural steel.

CHARACTERISTICS / ADVANTAGES

- Good adhesion on most aged, sound alkyd-, chlorinated rubber-, and epoxy coating.
- Cures even at temperatures down to -10°C.
- Excellent durability.
- tough, with long term flexibility.
- Good abrasion and impact resistance
- Extended maximum re-coating interval

PRODUCT INFORMATION

Packaging	SikaCor®-202 ET PT-A	11.5L
	SikaCor®-202 ET PT-B	3.5L
Appearance / Colour	White, Black and others	
Shelf life	12 months (Base & Hardener)	
Storage conditions	Store in original, unopened and undamaged sealed packaging in dry condition. Store cool and dry place avoiding direct exposure to sunlight.	
Density	Approx. 1.4 (kg/L)	
Flash Point	25°C	
Solid content by volume	62% ± 2	

SYSTEMS

Systems	1st coat : SikaCor® E Zinc-1	40-75 microns
	2nd coat : SikaCor®-100 EM	100 microns
	3rd coat : SikaCor®-202 ET	75-100 microns

APPLICATION INFORMATION

Mixing Ratio	Components A : B = 11.5 : 3.5 (by vol)
Thinner	SikaCor® E-thinner or SikaCor® Thinner-8, thinning less than 10% by volume.
Consumption	6.2 m ² /L (DFT 75 microns)
Substrate Temperature	During application and curing a substrate temperature should be kept above the dew point to avoid condensation. Relative humidity should be kept under 95%.
Surface Temperature	Above 5°C
Pot Life	Approx. 8 hours (at 20°C)
Waiting Time / Overcoating	Min. 12 hours at 20°C Max. : Unlimited
Drying time	Approx. 30 minutes (dry to touch, at 20°C)

APPLICATION INSTRUCTIONS

EQUIPMENT

AIRLESS SPRAY

- Nozzle orifice : 0.017-0.023 inch
- Nozzle pressure: Approx. 1900 psi

AIR-SPRAY

- Nozzle orifice : 1.8-2.0 mm
- Nozzle pressure : 40-60 psi

BRUSH/ROLLER

- For srtipe coating and spot repair only

SUBSTRATE PREPARATION

For one coat, direct to metal: as per relevant painting specification.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Korea Ltd.

135 gil 16, Nonhyun-ro
Gangnam-ku, Seoul, Korea
Tel : +82 2 6912 1500
Fax: +82 2 6912 1555
web: <http://kor.sika.com>



Product Data Sheet

SikaCor®-202 ET
March 2020, Version 01.01
020602000400000002

SikaCor-202ET-en-KR-(03-2020)-1-1.pdf