

PRODUCT DATA SHEET

Sikafloor®-17 Pronto

2-PART SEAL COAT FOR WET AREAS OR COLD STORAGE ROOMS BASED ON REACTIVE ACRYLIC RESINS

DESCRIPTION

Sikafloor®-17 Pronto is a two part, fast curing, flexible seal coat based on reactive acrylic resins, which is part of the Sikafloor® Pronto RB-25, Sikafloor® Pronto RB-28, Sikafloor® Pronto RB-55 and Sikafloor® Pronto RB-58 systems.

USES

Sikafloor®-17 Pronto may only be used by experienced professionals.

- Seal coat for broadcast layers of the Sikafloor®-Pronto Modular System (wet areas or cold storage rooms)
- Seal coat for broadcast screeds prepared of e.g. Sikafloor®-81 EpoCem® or Sikafloor®-263 SL if broadcast to excess (wet areas or cooling rooms)
- Particularly suitable for food industry use

CHARACTERISTICS / ADVANTAGES

- Very fast curing, even at low temperatures
- Good mechanical and chemical resistance
- Good UV-resistance
- Solvent-free
- Part of a complete modular system

APPROVALS / CERTIFICATES

- Conforms to the requirements of DIN 51130 (Skid / slip resistance).
- Certificate of conformity, 40893 U15, Isega Germany, October 2015.
- Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 01 05 007 0 000001 1131, and provided with the CE marking.
- Coating for surface protection of concrete according to EN 1504-2:2004, Declaration of Performance 02 08 01 05 007 0 000001 1131, certified by notified factory production control certification body 0921, certificate of conformity of the factory production control 1119, and provided with the CE marking.

PRODUCT INFORMATION

Composition	Reactive acrylic resins		
Packaging	Part A: Sikafloor®-17 Pronto	25 kg containers	200 kg drums
	Part B: Sika® Pronto Hardener	1.0 kg packs	(in 0.1 kg bags)
	Sika® Pronto Pigment	5 kg packs	(10 x 0.5 kg bags)
Appearance / Colour	Part A	Sikafloor®-17 Pronto	transparent, bluish liquid
	Part B	Sika® Pronto Hardener	white, powder
	Sika® Pronto Pigment: approx. 7032 other colours upon request		

Shelf life	From date of production:	
	Part A: Sikafloor®-17 Pronto	12 months
	Part B: Sika® Pronto Hardener	6 months
	Sika® Pronto Pigment	2 years
Storage conditions	The product must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C. Sikafloor® Pronto Hardener must be protected from heat, direct sunlight, moisture and impact.	
Density	~0.98 kg/l (at +23 °C)	(DIN 51 757)
Solid content by weight	~100 %	
Solid content by volume	~100 %	

TECHNICAL INFORMATION

Chemical Resistance	Resistant to many chemicals. Contact Sika technical service for specific information.	
Temperature Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 1 h	+80 °C
Short-term moist/wet heat* up to +80 °C where exposure is only occasional (steam cleaning etc.) *No simultaneous chemical and mechanical exposure and only in combination with Sikafloor®-14 / 15 Pronto as a broadcast system with approx. 3–4 mm thickness.		

SYSTEMS

Systems	Please refer to the system Data Sheet of :	
	Sikafloor® Pronto RB-24	Broadcast, fast curing system for wet areas
	Sikafloor® Pronto RB-27	Crack bridging waterproofing system for flooring applications

APPLICATION INFORMATION

Mixing Ratio	Part A : Pigment = 9 : 1 (by weight) The amount of Hardener required to be added on 9 kg Sikafloor®-17 Pronto is dependent on the ambient and substrate temperature.	
	Temperature	Sika® Pronto Hardener (% pbw)
	0 °C	270 g (3.0 %)
	+10 °C	180 g (2.0 %)
	+20 °C	90 g (1.0 %)
	+30 °C	90 g (1.0 %)
The hardener powder can also be ordered under the product name „Perkadox CH 50 X“ by Akzo Nobel, www.akzonobel.com , “Interlox BP-50 FT” by Degussa, www.degussa.com or “BP 50 W+” by Pergan GmbH, www.pergan.com .		
Consumption	~0.8–1.0 kg/m² depending on the system applied These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc. For detailed info, please refer to the system data sheet Sikafloor® Pronto RB-24, Sikafloor® Pronto RB-27.	
Ambient Air Temperature	0 °C min. / +30 °C max.	

Relative Air Humidity	~80 % r.h. max.	
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.	
Substrate Temperature	0 °C min. / +30 °C max.	
Pot Life	Temperature	Time
	0 °C	~ 20 minutes
	+10 °C	~ 20 minutes
	+20 °C	~ 15 minutes
	+30 °C	~ 8 minutes
Curing Time	Before applying Sikafloor®-17 Pronto on Sikafloor®-17 Pronto allow:	
	Substrate temperature	Minimum Maximum
	+0 °C	50 minutes *
	+10 °C	50 minutes *
	+20 °C	40 minutes *
	+30 °C	30 minutes *
* No time limits, the Sikafloor® Pronto materials can be applied on each other after thorough cleaning. Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity. For application on fully broadcast Sikafloor®-263 SL or similar screeds refer to the product data sheet of this material.		

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.
- Pull-off strength shall be not less than 1.5 N/mm²
- The application of a trial area is mandatory to ensure the compatibility of the substrate and the proposed Sikafloor Pronto System, especially when cementitious substrates treated with a curing agent.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Mix part A thoroughly then add the hardener in the correct quantity and mix for a further 1 minute.

Pigmented

Mix part A thoroughly. Premix the required amount of Sika® Pronto Pigment with the same quantity of part A by dissolver.

After that, mix part A and the obtained pigment paste with mixing ratio of 4 : 1 to get the final seal coat (overall content of Sika® Pronto Pigment in the final seal coat = 10 %) for at least 3 minutes. Then, add the hardener in the correct quantity and mix for further 1 minute.

Over mixing must be avoided to minimise air entrainment. For easy of handling, 25 kg units may be split (please refer to mixing table).

Always weight out components.

Mixing Tools

For indoor work, spark-free mixing equipment must be

used (explosion-proof)!

Sikafloor®-17 Pronto must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

For the preparation of the pigment powder, a dissolver must be used.

APPLICATION

Prior to application confirm relative air humidity and dew point.

For external applications, apply on a falling temperature. If applied during rising temperatures "pin holing" may occur from rising air.

Seal coat

Immediately after mixing, pour the Sikafloor®-17 Pronto onto the substrate and spread evenly by means of a "non-fuzzing" short-pile nylon roller or squeegee and then back-rolled (crosswise) with a short-piled roller.

A seamless finish can be achieved if a 'wet' edge is maintained during application.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

MAINTENANCE

To maintain the appearance of the floor after application, Sikafloor®-17 Pronto must have all spillages removed immediately and be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

FURTHER INFORMATION

Substrate quality & Preparation

Please refer to Sika Method Statement: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

Application instructions

Please refer to Sika Method Statement: "MIXING & APPLICATION OF FLOORING SYSTEMS".

Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

IMPORTANT CONSIDERATIONS

- Freshly applied Sikafloor®-17 Pronto must be protected from damp, condensation and water for at least 1 hour.
- Use spark proof mixing equipment for internal applications.
- Always ensure good ventilation when using Sikafloor®-17 Pronto in a confined space.
- For areas without frequent water load (approx. > 25% of time) or dry areas with temperatures > 0°C use Sikafloor-16 Pronto as a seal coat.
- In order to ensure optimum curing during internal applications the air must be exchanged at least seven times per hour. During application and curing use a forced fresh air supply / exhausting of fumes with appropriate equipment (spark-free / explosion-proof).
- Unevenness of substrates as well as inclusions of dirt cannot be covered by thin sealer coats. Therefore substrate and adjacent areas must be cleaned thoroughly prior to application.
- Systems based on reactive acrylic resins exhibit a characteristic odour during application and prior to achieving full cure, once fully cured they are taint free. All unpackaged goods should be removed from the area of the works during application. Do not apply in the presence of foodstuffs. Any foodstuffs, whether packaged or not, should be completely isolated from the flooring works during the application process and until the products are fully cured.
- For exact colour matching, ensure the Sika® -Pronto Pigment in each area is applied from the same control batch number.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

Tools

Recommended supplier of tools:

PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, www.polyplan.com

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

DIRECTIVE 2004/42/CE LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 500 g/l (Limit 2010) for the ready to use product. The maximum content of Sikafloor®-17 Pronto is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Korea Ltd.

135 gil 16, Nonhyun-ro
Gangnam-ku, Seoul, Korea
Tel : +82 2 6912 1500
Fax: +82 2 6912 1555
web: <http://kor.sika.com>



Product Data Sheet
Sikafloor®-17 Pronto
December 2018, Version 03.01
020813010030000001

Sikafloor-17Pronto-en-KR-(12-2018)-3-1.pdf